

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C08B 37/14, A61K 7/06, C11D 3/22</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 98/18828</b> <b>(43) International Publication Date:</b> 7 May 1998 (07.05.98)
<b>(21) International Application Number:</b> PCT/IB97/01325 <b>(22) International Filing Date:</b> 22 October 1997 (22.10.97)  <b>(30) Priority Data:</b> 08/736,866 25 October 1996 (25.10.96) US 08/738,290 25 October 1996 (25.10.96) US  <b>(71) Applicant:</b> RHONE-POULENC INC. [US/US]; Prospect Plains Road, Cranbury, NJ 08512-7500 (US).  <b>(72) Inventors:</b> CHOWDHARY, Manjit, Singh; 3 Cambridge Way, Princeton Junction, NJ 08550 (US). ROBINSON, Fred; 32 Cotton Wood Drive, Newtown, PA 18940 (US).  <b>(74) Agents:</b> SHEDDEN, John, A. et al.; Rhone-Poulenc Inc., Building N, Prospect Plains Road, Cranbury, NJ 08512-7500 (US).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> DERIVATIZED GUAR GUM COMPOSITION INCLUDING NONIONIC AND CATIONIC GROUPS WHICH DEMONSTRATE EXCELLENT SOLUTION CLARITY PROPERTIES FOR DETERGENT APPLICATIONS  <b>(57) Abstract</b>  Nonionic and cationic derivatized guar gum which demonstrates greater than 75 % light transmission at a wavelength of from about 500-600 nanometers when dispersed in water in the amount of 0.5 parts per 100 parts water and the process for producing such guar gum is disclosed. The compositions are particularly useful for producing products having utility in personal care and industrial cleaning products.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

DERIVATIZED GUAR GUM COMPOSITION INCLUDING NONIONIC AND CATIONIC  
GROUPS WHICH DEMONSTRATE EXCELLENT SOLUTION CLARITY PROPERTIES  
FOR DETERGENT APPLICATIONS

Background of the Invention

1. Field of the Invention

The present invention relates to polygalactomannan compositions and more particularly derivatized guar gum compositions including cationic groups which, when dispersed in water or other solvents to yield a highly viscous solution, are capable of forming a relatively transparent solution. The compositions are particularly useful for applications where clarity and purity of aqueous solutions are desirable such as oil recovery, personal care products, textile chemicals, paper chemicals, paints, and the like.

2. Technology Description

Natural and synthetic polymers containing hydroxy groups have been used as thickeners for foods, coatings, paints, explosive slurries, oil well fluids, cosmetics and other personal care products, and many other functional applications.

One class of polymers that have been widely used as suspending and viscosity agents are polygalactomannans. Polygalactomannans are polysaccharides composed principally of galactose and mannose units and are usually found in the endosperm of leguminous seeds such as guar, locust bean, honey locust, flame tree, and the like. The polygalactomannans may be used in either their natural form or may be substituted with one or more functional groups (e.g., carboxymethyl group). The most commonly used polygalactomannan is guar gum. In practice, to thicken a fluid the polygalactomannans may either be added by themselves, or with other viscosity modifiers such as other polysaccharides, xanthan gum and the like.

While the use of polygalactomannans, and guar gum in particular, as thickening agents has been met with great success, it is still desired to improve the physical properties of the guar gum when dispersed in a solution such as water. One such property is its ability to transmit light when used as an aqueous solution, and particularly one having a high viscosity having uses in personal care applications such as shampoos. Aqueous solutions of guar gum tend to be opaque or translucent at best.

It is particularly desired that clear, colorless and less impure solutions be produced when dispersing guar gum in water as it makes the final solution more useful for the above-described applications.

U.S. Patent No. 4,693,982 discloses the use of enzymes to reduce insolubles in guar gum. The level of clarity produced by the enzymatic treatment is not disclosed in the patent.

U.S. Patent No. 4,874,854 discloses low viscosity heteropolysaccharides, for example, guar gum. Example 3 discloses a "clarified" guar gum which is produced by cold filtration of a 0.3% solution through diatomaceous earth and precipitated with isopropyl alcohol. The ability of this material to transmit light is not disclosed in the patent.

U.S. Patent No. 3,912,713 discloses non-lumping derivatives of guar gum produced by derivatizing guar gum splits at a moisture content of 20-80% by weight, raising the moisture content of the splits, if necessary, to 30-80% by weight and fragmenting the splits by pressing them out in a thin layer and drying them on a cylinder heated to 100-180°C and comminuting the film to form particulates of a size in the order of +20 mesh, as measured by a Tyler screen, and preferably having a size of 2-5 mm. This process is commonly referred to as drum drying. According to Example 3, the product produced in the Example gives a "clear solution having no lumps or clots on stirring in water". No quantitative definition of "clear" (i.e. light transmittance) is presented in the patent.

U.S. Patent No. 4,057,509 discloses polygalactomannan allyl ether gels. According to Example 1, guar gum is purified to yield a material having less than 0.1% nitrogen content and about 0.48% ash. The same purification method is described in U.S. Patent No. 4,169,945.

U.S. Patent No. 4,659,911 teaches the treatment of 100 parts of guar gum with at least 150 parts of an aqueous alkali solution whereby the water present in the entire solution exceeds 60%. No data regarding the ability of resulting aqueous solutions to transmit light is set forth.

Commonly owned U.S. Patent Nos. 5,489,674 and 5,536,825 relate to a method for treating polygalactomannan splits to yield a product which, when dissolved in solution at 0.5 weight percent, is able to only provide light transparency, i.e., of greater than 75% at 500-600 nm. The method includes treating the splits in an aqueous alkaline solution followed by washing the splits in water or an organic solvent.

U.S. Patent Nos. 3,326,890; 3,350,386; and 3,483,121 are directed to methods for producing hydroxyalkyl polygalactomannans by using guar flour as a starting material. Included amongst the teachings is the suspension of guar flour in an organic, water-miscible solvent, and adding an alkaline material and an alkylene oxide to yield the final material.

For use in personal care applications such as soaps, body washes, shampoos and the like, it has been demonstrated that excellent performance benefits can occur when using polymeric materials containing cationic groups. This is particularly true in the case of clear personal compositions having increased viscosities (i.e., greater than about 500 centipoises).

Typically such personal care applications include inorganic salts such as NaCl or NH<sub>4</sub>Cl to provide viscosity to the final composition. The use of NaCl is preferred because it provides

added viscosity at a low cost without any off odor while being environmentally friendly. For use in combination with NaCl containing personal care products, a preferred cationic polymer has been quaternized hydroxyethyl cellulose. The use of cationic polygalactomannans would be particularly preferred because of their combination of thickening and environmentally friendly properties. However, it has been impossible to use cationic polygalactomannans in the past in conjunction with personal care products including inorganic salts because, when added, they produce a cloudy appearance, making them commercially undesirable.

Accordingly, there exists a need in the art for a derivatized guar gum, particularly one having cationic groups which is capable of producing nearly pure, clear and colorless solutions upon dispersing in water and a novel process for producing the gum.

#### Brief Summary of the Invention

In accordance with the present invention, cationically derivatized polygalactomannans which are capable of producing nearly pure, clear and colorless solutions upon dispersing in water or an organic solvent, especially those including NaCl, and a novel process for producing them is provided.

One embodiment of the present invention comprises nonionically and cationically derivatized polygalactomannans which demonstrate greater than 75% light transmission at a wavelength of from about 500-600 nanometers when dispersed in water in the amount of 0.5 parts per 100 parts water wherein the cationically derivatized polygalactomannans are produced by the process comprising the steps of:

- (a) contacting nonionically derivatized guar flour with an alcohol or an alcohol/water solution;
- (b) neutralizing the reaction mixture of step (a) with an acid;

(c) adding a cationic substituent in an amount such that the resulting material has a degree of substitution of the cationic substituent ranging from about 0.20 to about 1.0;

5

(d) adding an aqueous alkaline solution;

(e) washing the resulting mixture with water, an organic solvent or mixtures thereof; and

10

(f) recovering the product produced thereby.

In particular embodiments, the polygalactomannan produced includes both nonionic groups and cationic groups having specific molecular substitution and degrees of substitution respectively. In still other embodiments, the polygalactomannan produced may also include anionic groups, yielding an amphoteric material.

15

Another embodiment of the present invention comprises an oil field chemical, personal care chemical, industrial cleaning chemical, textile chemical, paper chemical or coating composition including the above-described cationically derivatized guar gum.

20

A third embodiment of the present invention comprises a process for producing a polygalactomannan comprising the steps of:

(a) contacting nonionically derivatized guar flour with an alcohol or an alcohol/water solution;

25

(b) neutralizing the reaction mixture of step (a) with an acid;

(c) adding a cationic substituent in an amount such that the resulting material has a degree of substitution of the cationic substituent ranging from about 0.20 to about 1.0;

30

(d) adding an aqueous alkaline solution;

(e) washing the resulting mixture with water, an organic solvent or mixtures thereof; and

5 (f) recovering the product produced thereby.

Still another embodiment of the present invention comprises a detergent composition useful for cleaning and/or conditioning human hair or skin or cleaning dishes or clothing which contains  
10 NaCl or  $\text{NH}_4\text{Cl}$  and further contains a nonionically and cationically derivatized polygalactomannan, the molecular substitution of the nonionic substituent being between about 0.4 and about 1.2 and the degree of substitution of the cationic substituent being between about 0.20 to about 1.0, said  
15 composition having a viscosity of greater than about 500 centipoises and said composition having greater than 75% light transmission at a wavelength of from about 500-600 nanometers.

Still another embodiment of the present invention comprises a  
20 detergent composition useful for cleaning and/or conditioning human hair or skin or cleaning dishes or clothing which contains NaCl or  $\text{NH}_4\text{Cl}$  and further contains a nonionically, anionically and cationically derivatized polygalactomannan, the molecular substitution of the nonionic substituent being between about  
25 0.14 and about 1.2, the degree of substitution of the anionic substituent being between about 0.10 to about 0.30 and the degree of substitution of the cationic substituent being between about 0.20 to about 1.0, said composition having a viscosity of greater than about 500 centipoises and said composition having  
30 greater than 75% light transmission at a wavelength of from about 500-600 nanometers.

Accordingly, it is an object of the present invention to provide a nonionically and cationically derivatized polygalactomannan  
35 which easily transmits light when used in an aqueous solution, has a low amount of insolubles, demonstrates excellent crosslinking properties, and can maintain a constant solution viscosity for an extended period of time.



It is another object of the present invention to provide an oil field chemical, food product, personal care or cosmetic chemical, absorbent material, textile chemical, paper chemical or coating composition which includes the novel derivatized polygalactomannan.

A further object of the present invention is to provide a process for making the derivatized polygalactomannan.

A still additional object of the present invention is to provide a detergent composition having excellent solution clarity and high viscosity.

These, and other objects, will readily be apparent to those skilled in the art as reference is made to the detailed description of the preferred embodiment.

#### Detailed Description of the Preferred Embodiment

In describing the preferred embodiment, certain terminology will be utilized for the sake of clarity. Such terminology is intended to encompass the recited embodiment, as well as all technical equivalents which operate in a similar manner for a similar purpose to achieve a similar result.

The present invention relates to novel polygalactomannans and the process for their manufacture. Polygalactomannans are polysaccharides composed principally of galactose and mannose units and are usually found in the endosperm of leguminous seeds, such as guar, locust bean, honey locust, flame tree, and the like. Guar flour, for example, is composed mostly of a galactomannan which is essentially a straight chain mannan with single membered galactose branches. The mannose units are linked in a 1-4- $\beta$ -glycosidic linkage and the galactose branching takes place by means of a 1-6 linkage on alternate mannose units. The ratio of galactose to mannose in the guar polymer is, therefore, one to two.

Locust bean gum is also a polygalactomannan gum of similar molecular structure in which the ratio of galactose to mannose is one to four. Guar and locust bean gum are the preferred  
5 sources of the polygalactomannans, principally because of the commercial availability thereof. In the preferred embodiment, the invention is directed to the production of guar gum.

The preferred guar starting material used in this invention is  
10 guar flour, which is often also referred to as guar powder, which has been derivatized with a nonionic substituent.

Preferred nonionic substituents are hydroxyalkyl, wherein alkyl represents a straight or branched hydrocarbon moiety having  
15 between 1 and about 6 carbon atoms (e.g., hydroxyethyl, hydroxypropyl, hydroxybutyl, etc.). The substituents are linked to the guar molecule by the reaction of the guar molecule with alkylene oxides (e.g., ethylene oxide, propylene oxide or butylene oxide). This reaction can take place when the guar is  
20 in the "splits" or "flour" form and is considered well known by those skilled in the art.

The term "molar substitution" as employed herein is the average number of moles of functional groups per anhydro sugar unit in  
25 the polygalactomannan gum. A particularly desired molar substitution of hydroxyalkyl groups is between about 0.01 and about 3.0, more preferably between about 0.14 to about 1.20. If the final polymer produced is cationic in nature, the molar substitution of the hydroxyalkyl groups should be between about  
30 0.40 to about 1.20, even more preferably between about 0.40 to about 0.80 whereas if the final polymer produced is amphoteric in nature, the molar substitution of the hydroxyalkyl groups should be between about 0.14 to about 1.20, even more preferably between about 0.14 to about 0.80. Preferred functional groups  
35 are the hydroxyethyl and hydroxypropyl groups.

Also considered within the scope of the invention is to use a starting material which includes one or more anionic groups. In

practice the anionic substituent will be a carboxyalkyl group wherein alkyl represents a straight or branched hydrocarbon moiety having between 1 and about 6 carbon atoms. Examples of such substituents include carboxymethyl, carboxyethyl and carboxypropyl groups and the like having a degree of substitution of between about 0.01 and about 3.0. Particularly preferred is the use of a carboxymethyl substituent having a degree of substitution of between about 0.1 and about 0.3.

The term "degree of substitution" as employed herein is the average substitution of functional groups per anhydro sugar unit in the polygalactomannan gum. In guar gum, the basic unit of the polymer consists of two mannose units with a glycosidic linkage and a galactose unit attached to the C6 hydroxyl group of one of the mannose units. On the average, each of the anhydro sugar units contains three available hydroxyl sites. A degree of substitution of three would mean that all of the available hydroxyl sites have been esterified with functional groups.

The above starting materials, and more specifically hydroxypropyl guar gum powder and carboxymethylhydroxypropyl guar gum are commonly available from manufacturers such as Rhône-Poulenc Inc. These materials are considered the starting materials for the present invention.

The starting nonionically substituted guar gum, or nonionically and anionically substituted guar gum in powder form, is then treated with an alcohol or an alcohol/water solution. In practice, the alcohol selected may be methanol, ethanol, isopropanol, n-propyl alcohol, n-butyl alcohol and the like. The alcohols may be used in neat (100%) form or in combination with water, the primary consideration being that the alcohol is miscible with water. Treatment is typically made at ambient temperatures, for example, about 30°C, although the temperature can be increased up to about 70°C while still obtaining efficacious results.

In practice it is generally preferred to use mixtures of water and organic solvents in this step. Particularly effective results occur when using between about 10 to about 90 percent water by weight and between about 90 to about 10 percent organic solvent by weight. Most preferred is the use of between about 5 80 to about 90% by weight isopropyl alcohol and between about 10 to about 20% by weight water. For example, excellent results have been obtained wherein the solution selected for use is an isopropanol/water mixture, wherein the respective amounts by 10 weight are 85% isopropanol and 15% water.

The amount of alcohol or alcohol water solution to be used in this step is that amount which is necessary to fully saturate the guar powder. In practice, this amount is usually at least 15 twice the amount by weight of the starting guar powder, and even more preferably, at least three times the amount by weight of the starting guar powder.

The resulting material will typically be alkaline. To improve 20 the clarity obtained when using the final product of the present invention, the alkaline material should be neutralized to a neutral pH (e.g., pH about 7). Any acid may selected for use to neutralize the solution, including strong acids such as hydrochloric acid and sulfuric acid or weak acids such as acetic 25 acid. In a preferred embodiment either hydrochloric or acetic acid is used. The amount of acid used is the amount necessarily for neutralization. Determination of this amount is accomplished by a simple acid/base analysis and is considered well within the skill in the art.


30 Treatment is typically made at ambient temperatures, for example, about 30°C.

After addition of the alcohol or alcohol/water solution and the 35 subsequent neutralization, followed by agitation as needed, a cationic reagent is added so that the guar gum is derivatized with one or more cationic groups. Cationic substituents include

primary, secondary, or tertiary amino groups or quaternary ammonium, sulfonium or phosphonium groups.

Illustrative cationic groups suitable for the practice of the present invention include quaternary ammonium groups. Typical of quaternary ammonium groups are tetramethylammonium chloride and bromide, benzyltrimethylammonium chloride and bromide, tetraethylammonium chloride and bromide, tetrabutylammonium chloride and bromide, methylpyridinium chloride and bromide, benzylpyridinium chloride and bromide, trimethyl-p-chlorobenzylammonium chloride and bromide, and the like, wherein each of the said groups is derivatized in the form of a radical which is substituted in a hydrocolloid gelling agent by means of an alkylene or oxyalkylene linkage.

In preferred embodiments, the quaternary ammonium ether substituents correspond to the formula



wherein  $\text{R}_1$  is a monohydroxylated or polyhydroxylated alkyl group containing between one and about six carbon atoms;  $\text{R}_2$  and  $\text{R}_3$  are independently, alkyl groups containing between one and about six carbon atoms;  $\text{R}_4$  is an alkyl group containing between one and about 24 carbon atoms; and  $\text{X}$  is a halide. The said alkyl groups can contain other atoms such as oxygen, sulfur and halogen.

Specific substituents include 2,3-epoxypropyl N,N,N-trimethylammonium chloride, 3-chloro-2-hydroxypropyl N,N,N-dodecyldimethylammonium chloride, 3-chloro-2-hydroxypropyl N,N,N-cocoalkyldimethylammonium chloride, and 3-chloro-2-hydroxypropyl N,N,N-octadecyldimethylammonium chloride. Such chemicals are commercially available from The Degussa Chemical Company under the trade names QUAB-151, QUAB-342, QUAB-360 and QUAB-426 respectively.

The amount of cationic reagent added to the guar powder is the amount that yields a cationic degree of substitution ranging from about 0.20 to about 1.0, and even more preferably between  
5 about 0.23 and about 0.80. Calculation of these amounts is easily obtained by simple stoichiometric equations and is considered well within the skill of the artisan.

To improve the reaction kinetics of the cationic substitution,  
10 an alkaline material is added as a catalyst. The alkaline material is typically aqueous solution of base, preferably an aqueous solution containing greater than 12% of NaOH, and more preferably a 12 to 60% aqueous solution of NaOH. Even more preferred is treatment with a 20% to a 50% aqueous solution. In  
15 the preferred embodiment between about 2 and about 50 parts of NaOH (100%) are added for every 100 parts of starting guar flour.

Thereafter, the temperature of the reaction mixture is increased  
20 to between about 40 and about 75°C, with a reaction temperature being between about 60 and about 70°C being even more preferred, and the mixture is stirred for a period of time sufficient to insure complete reaction of the reactants. In practice, this reaction time is between about one and about five hours, with a  
25 time of about three hours being more preferred.

Thereafter, the resulting material is neutralized to a neutral pH (e.g., pH about 7). Any acid may selected for use to neutralize the solution, including strong acids such as  
30 hydrochloric acid and sulfuric acid or weak acids such as acetic acid. In a preferred embodiment either hydrochloric or acetic acid is used. The amount of acid used is the amount necessarily for neutralization. Determination of this amount is accomplished by a simple acid/base analysis and is considered  
35 well within the skill in the art.

After the neutralization, the derivatized guar powder is filtered and then washed with water, an organic solvent, or a

mixture of both. Particularly preferred organic solvents are water miscible solvents including alcohols such as methanol, ethanol, isopropanol, n-propyl alcohol, n-butyl alcohol and the like. Other commonly used purification solvents such as acetone, glycols and the like may alternatively be selected. Of the above solvents, the most preferred is the use of methanol, ethanol, isopropyl alcohol, acetone and mixtures thereof.

The volume of the wash liquid is much greater than the amount of treated flour and can be performed in batchwise or multiple applications. In preferred practices the volume of the wash liquid is at least twice the volume of the treated flour and preferably at least three times the volume of the flour. It is preferable to conduct between 2 to 4 independent wash cycles. The concentration of the wash liquid for each cycle can be the same or different. For example washing of the powder may be accomplished by first washing with a dilute isopropyl alcohol solution, followed by washing with stronger solutions of isopropyl alcohol, and finally with acetone.

After washing, the derivatized guar powders are then dried and recovered using means known in the art. Examples of such means include air drying, filtering, evaporative drying, centrifuging, flash grinding, addition of solvents, freeze drying and the like. The use of fluidized bed drying is particularly recommended.

The resulting materials are particularly advantageous in that they are capable of achieving very high clarity when added to water in solution form. When added to water in 0.5% solutions, the inventive materials are capable of producing light transmissions of greater than 75% at 500-600 nm, with water being 100%. By using the inventive process, the guar gum produced can have a light transmission (0.5% solution) of greater than about 80%, more preferably greater than about 90%, and most preferably between about 93% and 100% (with water being 100%).

The compositions are also capable of producing high viscosity solutions while maintaining their clarity. For example a one percent solution of the inventive composition can yield a viscosity of between 300 and about 1000 centipoises using the  
5 above process. Increased viscosities can be obtained by conducting the reactions in an inert (e.g., nitrogen) environment.

Because of these above properties, the inventive materials are  
10 suitable for a wide range of commercial applications. Included amongst them are in oil and gas recovery, because of the low amount of enzymatic hydrolysis residues, high crosslinking ability, ease of filtration during natural gas recovery and potential synergy with other components such as cross-linking  
15 agents; personal care and industrial detergent products, because of low protein content, potentially improved skin sensitivity, clear and colorless appearance for consumer appeal, potential compatibility with other surfactants and personal care chemicals such as polyorganosiloxanes and potential flow  
20 modification characteristics; textile chemicals because of potential improved jet flow in textile machinery and increased molecular interaction with xanthan gum; dyes; paper chemicals including print and processing chemicals; paints; food products; explosives; absorbent materials; agricultural products;  
25 cosmetics; and any other application where the above combination of high clarity with high viscosity would be beneficial.

In addition, when crosslinked with agents such as borax as discussed above, the inventive compositions are able to provide  
30 extremely high crosslinked gels.

A particularly preferred use of the inventive compositions is in personal care compositions, more preferably in shampoos, body washes and in industrial cleaning compositions such as  
35 dishwashing detergents, laundry detergents and the like, where the thickening and light transmittance properties of the compositions can advantageously be utilized. In such formulations, the amount of the nonionic and cationic



derivatized polygalactomannan to be included is preferably between about 0.1 and about 2.0 percent by weight of the formulation, with amounts between about 0.3 and about 1.5 percent being more preferred and amounts between about 0.5 and about 1.0 percent by weight being most preferred.

In detergent compositions, the formulations used can typically include one or more surfactants in an aqueous carrier. The surfactants selected for use in producing such formulations are considered within the skill of the artisan and can be selected from nonionic, anionic, cationic, amphoteric and zwitterionic surfactants known in the art. Mixtures of the above surfactants may also be selected.

Examples of nonionic surfactants which may be selected include fatty acid amides, alkoxyated fatty alcohol amines, fatty acid esters, glycerol esters, alkoxyated fatty acid esters, sorbitan esters, alkoxyated sorbitan esters, alkylphenol alkoxyates, aromatic alkoxyates and alcohol alkoxyates.

Examples of anionic surfactants which may be selected include alkyl sulfates (alkyl is a fatty alkyl or alkylaryl group), ether sulfates, alkyl sulfonates, sulfosuccinates, sulfosuccinamates, naphthalene formaldehyde condensates, isethionates, taurates, phosphate esters and ether carboxylates.

Examples of cationic surfactants which may be selected include cationic quaternaries such as imidazolines arylalkyl quaternary compounds and aromatic quaternary compounds, amine oxides, and alkoxyated amines.

Examples of amphoteric surfactants which may be selected include betaines, sultaines, glycinate, amphoteric imidazoline derivatives and aminopropionates.

All of the above types of surfactants are commercially available and sold by Rhône-Poulenc Inc.

Also commonly included is an inorganic salt such as NaCl or NH<sub>4</sub>Cl to provide thickness to the final formulation. The use of NaCl is preferred because it has an extremely low cost. NaCl is typically present in amounts greater than about 0.5 percent by weight of the final formulation, and typically between about 0.5 to about 5.0 percent by weight of the final formulation, more preferably between about 1.0 to about 3.0 percent by weight of the final formulation. Also expressly considered as falling within the scope of the present inventions are products which utilize NH<sub>4</sub>Cl or other inorganic salts in place of NaCl.

However, a significant problem that has occurred in the past when trying to add cationic polygalactomannans to the final formulation of a personal care composition is that the presence of the NaCl (or NH<sub>4</sub>Cl) interacts with the cationic polygalactomannan resulting in an opaque solution. For aesthetic and market reasons, it is highly desirable to produce a clear formulation. It has been surprisingly discovered that the addition of the cationic polygalactomannans according to the present invention retain a clear appearance while providing added thickness properties. In addition, these materials are biodegradable, environmentally friendly, and mild to human hair and skin. Further, they can enable the production of a superior performing product. For example, shampoos in accordance with the present invention demonstrate superior combing and compatibility results as compared with those using commercially successful cationic polymers.

It has further been surprisingly discovered that only those nonionic and cationic derivatized polygalactomannans having the molecular substitution of the nonionic substituent being between about 0.4 and about 1.2 and the degree of substitution of the cationic substituent being between about 0.20 to about 1.0, or those nonionic, anionic and cationically derivatized polygalactomannans, the molecular substitution of the nonionic substituent being between about 0.14 and about 1.2, the degree of substitution of the anionic substituent being between about 0.10 to about 0.30 and the degree of substitution of the

cationic substituent being between about 0.20 to about 1.0 can effectively produce clear solutions when combined with personal care formulations containing NaCl. Compositions which do not have these respective molecular and degree of substitutions  
5 yield opaque solutions, making them commercially undesirable.

The formulation may also include optional additives such as perfumes, dyes, natural or synthetic fragrances, conditioning aids, and the like.

10

The final formulation will have a viscosity of greater than 500 centipoises, preferably between 1000 and about 25000 centipoises and most preferably between about 5000 and about 20000 centipoises. The final formulation will also preferably have a  
15 light transmission of greater than about 80%, more preferably greater than about 90%, and most preferably between about 93% and 100%.

The invention will be better understood by reference to the  
20 following examples.

#### Example 1

200 grams of JAGUAR® 8060 flour, a hydroxypropyl guar  
25 manufactured by Rhône-Poulenc Inc. having a molecular substitution of about 0.4 are added to 1000 ml. of an 85 percent isopropyl alcohol solution. The reaction is stirred for a few minutes and is neutralized with concentrated HCl or glacial acetic acid to neutralize a pH value of 7. Thereafter, 100 gms  
30 of 2,3-epoxypropyl N,N,N-trimethylammonium chloride are added over a 15 minute period and the mixture is stirred for an additional 15 minutes. 50 ml of a 50% NaOH solution are added over a 15 minute period and the mixture is stirred for an additional 15 minutes. Thereafter, the mixture is heated to 65°C  
35 and is held at 65°C for three hours. The mixture is cooled to about room temperature and is neutralized to a pH of about 7 by the addition of glacial acetic acid or HCl. The mixture is filtered and the filtered solids are washed successively with

one liter of 50% isopropyl alcohol aqueous solution, one liter of 85% isopropyl alcohol aqueous solution; one liter of 100% isopropyl alcohol, and one liter of acetone. The solids are then dried in a fluidized bed drier at about 60°C for about one hour.

5

The resulting composition is a nonionically and cationically derivatized guar gum having a molecular substitution of the nonionic substituent of about 0.4 and a degree of substitution of the cationic substituent of about 0.2. The solution viscosity of a 1% solution at 25°C is about 300-1500 cps as measured by a Brookfield Viscometer, 20 rpm and the light transmission of a 0.5% aqueous solution at 500-600 nm is greater than 90%.

10

#### Examples 2-29

15

The procedure of Example 1 is repeated except that different MS and DS values are obtained. Different molecular substitution (MS) values for the hydroxypropyl substituent are obtained by using different starting hydroxypropyl guar materials (in the case where MS=0, guar gum flour is used). Different degree of substitution (DS) values for the cationic substituent are obtained by using appropriate stoichiometric amounts of QUAB-151. The resulting materials are listed in the following Table.

25

Example	MS	DS
2	0.6	0.24
3	0.6	0.30
4	0.6	0.32
5	0.6	0.50
6	0.4	0.37
7	0.4	0.46
8	0.6	0.48
9	0.0	0.14

10	0.0	0.20
11	0.6	0.10
12	0.4	0.35
13	0.4	0.08
14	0.4	0.24
15	0.4	0.22
16	0.0	0.22
17	0.0	0.08
18	0.77	0.29
19	0.77	0.08
20	0.77	0.41
21	0.82	0.34
22	0.82	0.21
23	0.82	0.31
24	0.58	0.23
25	0.98	0.25
26	0.82	0.24
27	0.98	0.18
28	0.77	0.24
29	0.58	0.34

#### FORMULATION DATA AND TESTING

Each of the above Example Compositions are used in shampoo  
5 formulations. A first formulation includes the following  
components (amounts are listed by weight):

#### **Formulation One**

Component	Percent by Weight
Example Composition	0.5
Sodium Laureth. Sulfate (30% active solution)	10.0
coconut fatty acid amide (100% active)	2.5
NaCl	0, 2.0, 2.5 or 3.0
Water	Q.S.
TOTAL	100

The viscosity (in centipoises) and light transmittance (600 nm) for each of the formulations are shown in the following table. As a comparative example, a highly commercially successful polymer commonly used in clear shampoos, which is a quaternized hydroxyethyl cellulose having a molecular substitution of hydroxyethyl groups of 1.2 and a degree of substitution of cationic groups of 0.40 is selected for testing. This comparative example is referenced as CE. Each of the tested shampoos effectively functioned in their cleaning ability. However, their desirability would be limited by a low transmittance value, particularly in the presence of NaCl.

Ex.	0% NaCl	0% NaCl	2.0% NaCl	2.0% NaCl	2.5% NaCl	2.5% NaCl	3.0% NaCl	3.0% NaCl
	Vis.	% T	Vis.	% T	Vis.	% T	Vis.	% T
CE	60	99	4480	100	6500	100	9770	97
2	0	89	5230	97	7330	96	7280	94
3	0	99	2940	96	5800	96	7460	97
4	70	96	5590	99	8300	99	10000	99
5	20	96	4640	98	6680	96	7900	95
6	930	85	8850	95	15000	95	18000	93
7	not tested	not tested	not tested	not tested	19000	94	19000	96
8	not tested	not tested	not tested	not tested	14000	90	16000	87
9	820	41	8520	21	14000	10	16000	2
10	440	1	9180	12	18000	18	19000	24
11	280	97	7430	40	11000	2	13000	1
12	969	87	12000	96	17000	97	23000	96
13	40	99	4020	52	6650	2	8520	2
14	927	94	9350	96	16000	96	21000	98
15	893	78	13000	97	17000	97	22000	93
16	910	50	12000	64	17000	69	23000	73
17	1090	92	9100	2	12000	4	12000	6
18	571	96	8850	97	15000	97	22000	97

19	711	99	5760	1	9440	4	15000	5
20	720	93	12000	96	17000	96	22000	96
21	551	95	8300	97	14000	98	17000	98
22	721	97	6900	98	15000	96	18000	94
23	927	96	13000	96	18000	98	23000	99
24	1430	96	22000	98	29000	98	30000	98
25	6330	96	15000	89	15000	91	13000	67
26	671	87	9270	98	15000	98	17000	98
27	782	97	9020	98	15000	97	16000	75
28	835	97	8520	97	13000	95	18000	94
29	830	95	12000	94	16000	98	19000	98



A second formulation includes the following components (amounts are listed by weight):

5    **Formulation Two:**

Component	Percent by Weight
Example Composition	0.5
Sodium Laureth Sulfate (30% active solution)	10.0
cocoamidopropyl betaine (30% active)	2.5
NaCl	0, 1.0, 1.5 or 2.0
Water	Q.S.
TOTAL	100

The viscosity (in centipoises) and light transmittance (600 nm) for each of the formulations are shown in the following table. As a comparative example, a highly commercially successful polymer commonly used in clear shampoos, which is a quaternized hydroxyethyl cellulose having a molecular substitution of hydroxyethyl groups of 1.2 and a degree of substitution of cationic groups of 0.40 is selected for testing. This comparative example is referenced as CE. Each of the tested shampoos effectively functioned in their cleaning ability. However, their desirability would be limited by a low transmittance value, particularly in the presence of NaCl.

Ex.	0% NaCl	0% NaCl	2.0% NaCl	2.0% NaCl	2.5% NaCl	2.5% NaCl	2.5% NaCl	3.0% NaCl	3.0% NaCl
CE	90	99	1800	99	4840	99	16000	94	
2	0	97	3110	97	12000	84	24000	90	
3	30	98	1190	97	4980	95	14000	96	
4	140	98	3320	98	10000	95	18000	97	
5	100	98	3460	97	10000	97	21000	97	
6	1110	93	5110	96	14000	95	29000	95	
7	not tested	not tested	not tested	not tested	16000	95	36000	96	
8	not tested	not tested	not tested	not tested	18000	82	39000	80	
9	1050	43	53000	15	15000	7	32000	2	
10	1090	3	6200	18	18000	25	37000	17	
11	440	94	4660	8	9270	1	33000	1	
12	1390	94	6900	97	18000	97	38000	98	
13	140	99	2610	5	9100	2	24000	1	
14	1390	96	6210	97	17000	96	33000	95	
15	1120	93	4830	94	14000	97	32000	97	
16	1180	52	5860	62	13000	62	33000	62	
17	1430	96	4480	2	8430	2	28000	2	
18	1010	96	5040	95	14000	92	35000	81	
19	1030	96	3420	2	11000	4	26000	2	

20	1040	94	6500	94	16000	94	39000	95
21	1080	96	5460	97	16000	96	35000	98
22	1030	98	4790	98	15000	96	31000	86
23	902	97	3560	98	8680	98	23000	98
24	1140	97	4830	96	10000	80	26000	62
25	1000	98	5060	98	13000	85	30000	74
26	690	96	3120	98	7900	98	17000	99
27	860	98	3520	98	9200	48	23000	1
28	1120	97	4510	97	13000	97	28000	96
29	977	96	5560	98	16000	98	31000	98

COMB TESTING

- 5 To determine if the formulations would effectively provide functional properties to human hair a Diastrom Wet Combing Test is performed on each of the following Formulation Three Samples.

## 10 Formulation Three:

Component	Parts by Weight
Example Composition	10.0
Sodium Laureth Sulfate (30% active solution)	600.0
cocoamidopropyl betaine (30% active)	199.0
coconut fatty acid amide (100% active)	169.0
NaCl	30.0
Formalin	2.0
Water	Q.S.
TOTAL	2000

- 15 This industrial standard test measures the difference between the peak force used to comb treated human hair treated with the experimental shampoos as compared to the peak force used to comb human hair which has only been wetted with water. A working area is obtained by measuring the area under the force curve obtained for the test compositions as compared to that of the water only treated hair. A positive value for both peak value and work value is considered desirable. The results are shown
- 20 in the following Table.

Sample	Peak Value	Work Area
CE	7	11
2	not tested	not tested
3	3	7
4	12	10
5	-1	0
6	-2	0

7	7	7
8	5	-2
9	32	32
10	24	26
11	31	29
12	16	17
13	48	45
14	12	14
15	14	12
16	4	6
17	49	48
18	30	26
19	30	28
20	3	-2
21	4	-2
22	9	10
23	-7	-7
24	0	-1
25	2	3
26	-8	-9
27	10	12
28	8	7
29	6	8

The above data demonstrates that the molecular substitution of  
 the nonionic substituent being between about 0.4 and about 1.2  
 5 and the degree of substitution of the cationic substituent being  
 between about 0.20 to about 1.0, yields a composition having a  
 viscosity of greater than about 500 centipoises and having  
 greater than 75% light transmission at a wavelength of from  
 about 500-600 nanometers. In addition, the resulting personal  
 10 care compositions have excellent detergency, mildness and  
 combing properties.

Example 30

200 grams of carboxymethylhydroxypropyl guar manufactured by Rhône-Poulenc Inc. having a molecular substitution of about 0.2 and a degree of substitution of carboxymethyl groups of about 0.1 are added to 1000 ml. of an 85 percent isopropyl alcohol aqueous solution. The reaction is stirred for a few minutes and concentrated HCl or glacial acetic acid is added to neutralize the pH to a value of 7. Thereafter, 120 grams of 2,3-epoxypropyl N,N,N-trimethylammonium chloride are added over a 15 minute period and the mixture is stirred for an additional 15 minutes. 60 ml of a 5% NaOH solution are added over a 15 minute period and the mixture is stirred for an additional 15 minutes. Thereafter, the mixture is heated to 65°C and is held at 65°C for three hours. The mixture is cooled to about room temperature and is neutralized to a pH of about 7 by the addition of concentrated hydrochloric acid or glacial acetic acid. The mixture is filtered and the filtered solids are washed successively with one liter of 50% isopropyl alcohol aqueous solution, one liter of 85% isopropyl alcohol aqueous solution, one liter of 100% isopropyl alcohol, and one liter of acetone. The solids are then dried in a fluidized bed drier at about 60°C for about sixty minutes.

The resulting composition is a nonionically, anionically and cationically derivatized guar gum having a molecular substitution of the nonionic substituent of about 0.2, a degree of substitution of the anionic substituent of about 0.1., and a degree of substitution of the cationic substituent of about 0.4.

The solution viscosity of a 1% solution at 25°C is 300-1500 cps as measured by a Brookfield Viscometer, 20 rpm, and the light transmission of a 0.5% aqueous solution at 500-600 nm is greater than 90%. It is believed that this composition could effectively be used in personal care or industrial detergent applications which include NaCl and yield a highly viscous clear product.

Having described the invention in detail and by reference to the preferred embodiments thereof, it will be apparent that modifications and variations are possible without departing from  
5 the scope of the appended claims.

## WHAT IS CLAIMED IS:

1. Polygalactomannans which contain both nonionic and cationic groups and demonstrate greater than 75% light transmission at a wavelength of from about 500-600 nanometers when dispersed in water in the amount of 0.5 parts per 100 parts water wherein the nonionically and cationically derivatized polygalactomannans are produced by the process comprising the steps of:
  - (a) contacting guar flour containing nonionic groups with an alcohol or an alcohol/water solution;
  - (b) neutralizing the reaction mixture of step (a) with an acid;
  - (c) adding a cationic substituent in an amount such that the resulting material has a degree of substitution of cationic groups ranging from about 0.20 to about 1.0;
  - (d) adding an aqueous alkaline solution;
  - (e) washing the resulting mixture with water, an organic solvent or mixtures thereof; and
  - (f) recovering the product produced thereby.
2. The polygalactomannans according to claim 1 wherein said nonionic groups comprise hydroxyalkyl groups, wherein alkyl represents a straight or branched hydrocarbon moiety having between 1 and about 6 carbon atoms.
3. The polygalactomannans according to claim 2 wherein said nonionic groups are selected from the group consisting of hydroxyethyl and hydroxypropyl.




4. The polygalactomannans according to claim 2 wherein said nonionic groups have a molecular substitution between about 0.4 and about 1.2.

5 5. The polygalactomannans according to claim 1 wherein said cationic groups are quaternary groups.

6. The polygalactomannans according to claim 5 wherein cationic substituents are of the formula

10



15

wherein  $R_1$  is a monohydroxylated or polyhydroxylated alkyl group containing between one and about six carbon atoms;  $R_2$  and  $R_3$  are  
20 independently, alkyl groups containing between one and about six carbon atoms;  $R_4$  is an alkyl group containing between one and about 24 carbon atoms; and  $X$  is a halide.

7. The polygalactomannans according to claim 1 wherein said  
25 cationic groups have a degree of substitution between about 0.23 and about 0.80.

8. The polygalactomannans according to claim 1 wherein said  
polygalactomannans further comprise anionic groups.

30

9. The polygalactomannans according to claim 8 wherein said anionic groups comprise carboxyalkyl groups wherein alkyl represents a straight or branched hydrocarbon moiety having between 1 and about 6 carbon atoms.

35

10. The polygalactomannans according to claim 9 wherein said anionic groups comprise carboxymethyl groups.

11. A process for producing polygalactomannans which contain both nonionic and cationic groups and demonstrate greater than 75% light transmission at a wavelength of from about 500-600 nanometers when dispersed in water in the amount of 0.5 parts per 100 parts water comprising the steps of:

(a) contacting guar flour containing nonionic groups with an alcohol or an alcohol/water solution;

(b) neutralizing the reaction mixture of step (a) with an acid;

(c) adding a cationic substituent in an amount such that the resulting material has a degree of substitution of cationic groups ranging from about 0.20 to about 1.0;

(d) adding an aqueous alkaline solution;

(e) washing the resulting mixture with water, an organic solvent or mixtures thereof; and


(f) recovering the product produced thereby.

12. The process according to claim 11 wherein said nonionic groups comprise hydroxyalkyl groups, wherein alkyl represents a straight or branched hydrocarbon moiety having between 1 and about 6 carbon atoms.

13. The process according to claim 12 wherein said nonionic groups have a molecular substitution between about 0.4 and about 1.2.

14. The process according to claim 11 wherein said cationic groups are quaternary groups.

15. The process according to claim 14 wherein cationic substituents are of the formula



wherein  $R_1$  is a monohydroxylated or polyhydroxylated alkyl group containing between one and about six carbon atoms;  $R_2$  and  $R_3$  are independently, alkyl groups containing between one and about six carbon atoms;  $R_4$  is an alkyl group containing between one and about 24 carbon atoms; and  $X$  is a halide.

16. The process according to claim 14 wherein said cationic groups have a degree of substitution between about 0.23 and about 0.80.

17. The process according to claim 11 wherein said polygalactomannans further comprise anionic groups.

18. The process according to claim 17 wherein said anionic groups comprise carboxyalkyl groups wherein alkyl represents a straight or branched hydrocarbon moiety having between 1 and about 6 carbon atoms.

19. An oil field chemical, personal care chemical, industrial cleaning chemical, textile chemical, paper chemical or coating composition including polygalactomannans which contain both nonionic and cationic groups and demonstrate greater than 75% light transmission at a wavelength of from about 500-600 nanometers when dispersed in water in the amount of 0.5 parts per 100 parts water wherein the nonionically and cationically derivatized polygalactomannans are produced by the process comprising the steps of:

(a) contacting guar flour containing nonionic groups with an alcohol or an alcohol/water solution;

(b) neutralizing the reaction mixture of step (a) with an acid;

(c) adding a cationic substituent in an amount such that the resulting material has a degree of substitution of cationic groups ranging from about 0.20 to about 1.0;

(d) adding an aqueous alkaline solution;

(e) washing the resulting mixture with water, an organic solvent or mixtures thereof; and

(f) recovering the product produced thereby.

20. The composition according to claim 19 having a greater than 90% light transmission at a wavelength of from about 500-600 nanometers

21. A detergent composition useful for cleaning and/or conditioning human hair or skin or cleaning dishes or clothing which contains NaCl or NH<sub>4</sub>Cl and further contains a nonionically and cationically derivatized polygalactomannan, the molecular substitution of the nonionic substituent being between about 0.4 and about 1.2 and the degree of substitution of the cationic substituent being between about 0.20 to about 1.0, said detergent composition having a viscosity of greater than about 500 centipoises and said composition having greater than 75% light transmission at a wavelength of from about 500-600 nanometers.

22. The composition according to claim 21 which is selected from the group consisting of personal care compositions and industrial cleaning compositions.

23. The composition according to claim 22 comprising a personal care composition useful for cleaning and/or conditioning human hair or skin.


24. The composition according to claim 23 wherein the composition includes NaCl present in an amount of between about 0.5 and about 3.0 percent by weight of the composition.

25. The composition according to claim 21 wherein said nonionic substituent comprises hydroxyalkyl groups, wherein alkyl represents a straight or branched hydrocarbon moiety having between 1 and about 6 carbon atoms.

26. The composition according to claim 25 wherein said nonionic substituents are selected from the group consisting of hydroxyethyl and hydroxypropyl.

27. The composition according to claim 21 wherein said cationic groups are quaternary groups.

28. The composition according to claim 27 wherein said cationic substituents are of the formula



wherein  $\text{R}_1$  is a monohydroxylated or polyhydroxylated alkyl group containing between one and about six carbon atoms;  $\text{R}_2$  and  $\text{R}_3$  are independently, alkyl groups containing between one and about six carbon atoms;  $\text{R}_4$  is an alkyl group containing between one and about 24 carbon atoms; and  $\text{X}$  is a halide.

29. The composition according to claim 21 wherein said cationic substituents have a degree of substitution between about 0.23 and about 0.80.

30. The composition according to claim 21 wherein said nonionically and cationically derivatized polygalactomannan is present in an amount of about 0.1 and about 2.0 percent by weight of the composition.

5

31. The composition according to claim 21 having a greater than 90% light transmission at a wavelength of from about 500-600 nanometers.

10 32. A detergent composition useful for cleaning and/or conditioning human hair or skin or cleaning dishes or clothing which contains NaCl or  $\text{NH}_4\text{Cl}$  and further contains a nonionically, anionically and cationically derivatized polygalactomannan, the molecular substitution of the nonionic substituent being between  
15 about 0.14 and about 1.2, the degree of substitution of the anionic substituent being between about 0.10 to about 0.30 and the degree of substitution of the cationic substituent being between about 0.20 to about 1.0, said composition having a viscosity of greater than about 500 centipoises and said  
20 composition having greater than 75% light transmission at a wavelength of from about 500-600 nanometers.

33. The composition according to claim 32 which is selected from the group consisting of personal care compositions and  
25 industrial cleaning compositions.

34. The composition according to claim 33 comprising a personal care composition useful for cleaning and/or conditioning human hair or skin.

30

35. The composition according to claim 34 wherein the composition includes NaCl present in an amount of between about 0.5 and about 3.0 percent by weight of the composition.


35 36. The composition according to claim 32 wherein said nonionic substituent comprises hydroxyalkyl groups, wherein alkyl

represents a straight or branched hydrocarbon moiety having between 1 and about 6 carbon atoms.

37. The composition according to claim 36 wherein said nonionic substituents are selected from the group consisting of hydroxyethyl and hydroxypropyl.

38. The composition according to claim 32 wherein said cationic groups are quaternary groups.

39. The composition according to claim 38 wherein said cationic substituents are of the formula



wherein  $\text{R}_1$  is a monohydroxylated or polyhydroxylated alkyl group containing between one and about six carbon atoms;  $\text{R}_2$  and  $\text{R}_3$  are independently, alkyl groups containing between one and about six carbon atoms;  $\text{R}_4$  is an alkyl group containing between one and about 24 carbon atoms; and  $\text{X}$  is a halide.

40. The composition according to claim 32 wherein said cationic substituents have a degree of substitution between about 0.23 and about 0.80.

41. The composition according to claim 32 wherein said anionic groups comprise carboxyalkyl groups wherein alkyl represents a straight or branched hydrocarbon moiety having between 1 and about 6 carbon atoms.

42. The composition according to claim 41 wherein said anionic groups comprise carboxymethyl groups.

43. The composition according to claim 32 having a greater than 90% light transmission at a wavelength of from about 500-600 nanometers.



# INTERNATIONAL SEARCH REPORT

International Application No

PCT/IB 97/01325

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08B37/14 A61K7/06 C11D3/22

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08B A61K C11D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 686 643 A (RHONE-POULENC INC.) 13 December 1995 see page 6, line 39 - page 7, line 45; example 8 ---	1-43
X	EP 0 331 472 A (HI-TEK POLYMERS) 6 September 1989 see page 2, line 50 - line 54 see page 3, line 47 - line 50 ---	1-20
A	PATEL S P ET AL: "SYNTHESIS AND CHARACTERIZATION OF QUATERNARY AMMONIUM COMPOUNDS OF GUAR GUM AND HYDROXYETHYL GUAR GUM" STARCH STARKE, vol. 41, no. 5, May 1989, pages 192-196, XP000026584 --- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

27 January 1998

Date of mailing of the international search report

04/02/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040. Tx. 31 651 epo nl.  
Fax: (+31-70) 340-3016

Authorized officer

Lensen, H

# INTERNATIONAL SEARCH REPORT

Int. l. Application No

PCT/IB 97/01325

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>PATENT ABSTRACTS OF JAPAN vol. 95, no. 2, 31 March 1995 &amp; JP 06 312915 A (TSUMURA &amp; CO), 8 November 1994, see abstract</p> <p>---</p>	
A	<p>PATENT ABSTRACTS OF JAPAN vol. 8, no. 205 (C-243), 19 September 1984 &amp; JP 59 096103 A (MITSUBISHI ACETATE), 2 June 1984, see abstract</p> <p>-----</p>	

# INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. tional Application No

PCT/IB 97/01325

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 686643 A	13-12-95	US 5489674 A	06-02-96
		US 5536825 A	16-07-96
		AU 684006 B	27-11-97
		AU 2058395 A	21-12-95
		BR 9502720 A	30-04-96
		CA 2151349 A	10-12-95
		JP 8085702 A	02-04-96
		NZ 272306 A	25-06-96
EP 331472 A	06-09-89	US 4918181 A	17-04-90
		CA 1308710 A	13-10-92
		DE 68910348 D	09-12-93
		DE 68910348 T	17-03-94
		JP 1282202 A	14-11-89
		JP 2639058 B	06-08-97